

















Features/Applications

GREMTUBE® ES 180 is a very flexible extruded Silicone tubing.

GREMTUBE® ES 180 offers high temperature performances up to 220°C, a good mechanical protection and an excellent dielectric properties. It has a an excellent weather resistance and it is hydrophobic.

GREMTUBE® ES 180 is suitable for electrical insulation with high temperature where high flexibility is required.

Various

Standard colour: Clear.

Special sizes and colours available on request.

Dimensions

Reference	Inside Diameter (mm)	External	Standard Length
GREMTUBE® ES 180	Nom.	Diameter (mm) Nom.	(m)
0,5 x 1,2	0,5	1,2	250
0,8 x 1,6	0,8	1,6	250
1 x 1,8	1,0	1,8	250
1,5 x 2,3	1,5	2,3	250
1,7 x 2,5	1,7	2,5	250
2 x 3	2,0	3,0	250
2,5 x 3,5	2,5	3,5	250
3 x 4	3,0	4,0	100
4 x 5	4,0	5,0	100
4,5 x 5,5	4,5	5,5	100
5 x 6	5,0	6,0	100
6 x 7	6,0	7,0	100
7 x 8	7,0	8,0	100
8 x 9	8,0	9,0	100
9 x 10	9,0	10,0	100
10 x 11	10,0	11,0	100
12 x 13,2	12,0	13,2	100
14 x 15,2	14,0	15,2	50
16 x 18	16,0	18,0	50
18 x 20	18,0	20,0	50
20 x 22	20,0	22,0	25
22 x 24	22,0	24,0	25
24 x 26	24,0	26,0	25
26 x 28	26,0	28,0	25
28 x 30	28,0	30,0	25
31,7 x 34,9	31,7	34,9	25
38,1 x 41,3	38,1	41,3	20
44,5 x 48,5	44,5	48,5	20
50,8 x 54,9	50,8	54,9	20
54 x 58	54,0	58,0	20
96 x 100	96,0	100,0	10

Spools as standard, cut pieces available on request

Property Values Test Methods Physical -80°C to +220°C Working temperature Peak temperature +250°C 70 Shores A DIN 53505 Hardness ≥ 10 MPa Tensile strength DIN 53504 S1 ≥ 400% Elongation at break 20 kV/mm NF EN 60684-2 **Electrical** Dielectric strength Volume resistivity $\geq 10^{14} \; \Omega.cm$ ASTM D 257 Chemical Weather resistance Excellent

04/07/2022 Rev0

Whilst every attempt is made to provide data that is as accurate as possible the values provided should be treated as a guide only. It remains the responsibility of the user to test the product and determine suitability. GREMTEK shall not be held responsible for any loss or defect resulting from incorrect, improper or inappropriate use of this product.



Recommended storage

conditions: Keep in cool, dry, ventilated storage (maximum temperature

of 35°C) and in closed containers.

REACH

compliant