



Features/Applications

GREMTUBE® GHW and GHWA are halogen free, heavy wall, cross linked Polyolefin heat shrink tubing (GHW), with adhesive (GHWA).

GREMTUBE® GHW and GHWA offer good electrical insulation properties, high resistance to impact, abrasion and are UV resistant. The 3:1 shrink ratio allows the tubing to fit over irregular shapes and large connectors.

GREMTUBE® GHW and GHWA are suitable for a variety of medium voltage (up to 36 kV) electrical equipment and cable connections in wet environments such as marine vessels, offshore oil platforms, shipyard and harbor applications when zero halogen properties are required.

Various

Standard colours: Black.

Flame retardant version is available on request (GREMTUBE® GHW-FR / GHWA-FR)

Specifications

UV resistant.

Dimensions



Reference	As supplied (mm)	After full recovery (mm)		Standard Length (m)
GREMTUBE® GHW / GHWA	Inside Diameter Min. (D)	Inside Diameter Max. (d)	Total Wall Thickness Nom. (t)	
009,0	9,0	3,0	2,60	1,2
012,0	12,0	4,0	2,80	1,2
016,0	16,0	5,0	3,00	1,2
019,0	19,0	6,0	3,00	1,2
022,0	22,0	6,0	3,25	1,2
025,0	25,0	8,0	3,25	1,2
028,0	28,0	6,0	3,25	1,2
033,0	33,0	8,0	3,25	1,2
035,0	35,0	12,0	3,95	1,2
040,0	40,0	12,0	3,95	1,2
045,0	45,0	13,0	3,95	1,2
055,0	55,0	16,0	4,05	1,2
065,0	65,0	19,0	4,05	1,2
075,0	75,0	22,0	4,05	1,2
085,0	85,0	25,0	4,05	1,2
095,0	95,0	25,0	4,05	1,2
105,0	105,0	30,0	4,05	1,2
115,0	115,0	34,0	4,05	1,2
130,0	130,0	36,0	4,05	1,2
140,0	140,0	42,0	4,05	1,2
160,0	160,0	50,0	4,05	1,2
175,0	175,0	58,0	4,05	1,2
200,0	200,0	65,0	4,05	1,2
230,0	230,0	75,0	4,05	1,2

● Cut pieces are available on request

Property

		Values	Test Methods
Physical	Working temperature	-55°C to +105°C	-
	Longitudinal change	-10% to 0%	-
	Tensile strength	≥ 12 MPa	ASTM D 2671
	Elongation at break	Unaged ≥ 400%	
	Tensile strength	Aged (168h @ 150°C) ≥ 12 MPa	ASTM D 2671
	Elongation at break	≥ 350%	
	Heat shock (Outer jacket)	4h @ 200°C No dripping or flowing	ASTM D 2671
Electrical	Low temperature flexibility	4h @ -55°C No cracking	ASTM D 2671
	Dielectric strength	≥ 15 kV/mm	ASTM D 2671
	Volume resistivity	≥ 10 ¹⁴ Ω.cm	ASTM D 2671
Adhesive	Peel strength to steel	80 N/25 mm	ASTM D 2671
	Peel strength to XLPE	110 N/25 mm	ASTM D 2671

Recommended storage conditions: Keep in cool, dry, ventilated storage (maximum temperature of 35°C) and in closed container.

25/08/2026 Rev6

Whilst every attempt is made to provide data that is as accurate as possible the values provided should be treated as a guide only. It remains the responsibility of the user to test the product and determine suitability. GREMTEK shall not be held responsible for any loss or defect resulting from incorrect, improper or inappropriate use of this product.